



## TECHNICAL DATA SNOWBULK

<b>Parameter</b>	<b>Value</b>	<b>Tolerance</b>	<b>Comment</b>
Basis Weight	50 to 90 g/m <sup>2</sup>	+/- 4 g/m <sup>2</sup>	As specified by Customer
Bulk / Volume	1.6 / 16 to 2.4 / 24		As specified by Customer
Caliper	80 to 180 micron	+/- 3 micron	180 micron maximum
Brightness	70 iso	+/- 0.75	
Shade	7.5 (Cream) or 4 (Blue/White)	+/- 0.5	Cream or Blue White
Opacity	88 to 96	+/- 1	Dependant on grammage/caliper
Moisture	8%	+/- 0.5	
Tear	240 to 450 Nm	+/- 0.4	
Tensile	2.40 to 4.50 kN/m	+/- 0.4	
Main furnish	85 to 90% mechanical groundwood		
Secondary furnish	10 to 15% Cellulose		
Wrapping	Kraft wrappers		2 layers
Cores	76mm strawboard		152mm cores on request
Joins	Maximum 2 joins per reel		Marked by red line on reel
Reel Diameter	1000mm or 1150mm		As specified by customer
Accreditation	FSC	Volume Credit	FSC Paper on request

All paper supplied according to the General Trade Rules for the supply of paper and paperboard.

Should Technical Data be required for a specific grammage / caliper combination these can be provided upon request.